

# GreenGuard®

## SuperStretch Acrylic Flashing

Premium waterproof flashing for sealing around and conforming to windows, doors and other building penetrations



- Stretches to fit arched windows, corners and round protrusions
- High-tack adhesive sticks firmly to most common building materials, including OSB.
- Specially formulated to bond even to damp surfaces.
- Works in a wide range of temperatures—sticks well in both cold and hot conditions.
- Won't melt or stain in high summer heat.
- Proprietary backing seals tightly around nails and staples to block moisture.

## Description

This super flexible tape seals tightly around nails, staples, and rough surfaces. Its thin design keeps it from piling up at corners and overlaps, so installing siding and windows is a lot easier. The split backing makes it simple to peel and stick right where you need it. Meets AAMA 711-05 and ICC Division 7, Evaluation ESR-2797.

## Installation

To obtain the best adhesion, Kingspan GreenGuard® SuperStretch™ Acrylic Flashing should be installed when outdoor temperatures range from 0° to 150°F ( -18° to 66° C) over surfaces that are free of dirt and moisture. This product contains a pressure sensitive adhesive. Placement by hand, then it is necessary to apply strong pressure with a j-roller to ensure adhesion. Kingspan GreenGuard® SuperStretch™ Acrylic Flashing may remain exposed for up to 12 months.

## Specifications

- Withstands UV exposure for up to 12 months
- Installs easily in extreme temperatures—from as low as 0°F (-18°C) to as high as 150°F (66°C).
- Compatible with a wide range of building sealants, including synthetic rubber, butyl, polyurethane, silicone, and silane-terminated hybrid sealants—no adverse reactions.
- Split release liner allows for quick, accurate positioning and easy application.

## Compliance

- Meets AAMA 711-05 standards for self-adhering flashing used in installing exterior wall fenestration products.
- Rated Type A for adhesion—no primer needed under tested conditions.
- Achieves Class 3 Thermal Exposure, the highest level (176°F / 80°C for 7 days).
- Passes nail sealability tests (ASTM D1970 and ASTM E331/547), both before and after thermal cycling, as specified in AAMA 711-05 Annex 1.

## Handling & Storage

Store boxes containing Kingspan GreenGuard® SuperStretch™ Acrylic Flashing in a clean, dry area without prolonged, direct exposure to sunlight. SuperStretch™ Acrylic Flashing has a shelf life of 24 months.

**WARNING:** This product is combustible. A protective barrier or thermal barrier is required as specified in the appropriate building code. Protect it from exposure to open flame or other ignition sources during shipping, storage and installation.

**WARNING:** The release paper of Kingspan GreenGuard® SuperStretch™ Acrylic Flashing is slippery and should not be walked on at any time. Discard release paper in a designated container.

## Kingspan Insulation LLC

6120 Powers Ferry Road NW | Suite 350  
Atlanta | Georgia 30339

T: +1 (678) 831 7526

E: [info@kingspaninsulation.us](mailto:info@kingspaninsulation.us)

[www.kingspaninsulation.us](http://www.kingspaninsulation.us)

[www.kingspaninsulation.ca](http://www.kingspaninsulation.ca)

© Kingspan, the G Device and the Lion Device are Registered Trademarks of the Kingspan Group plc in the US, Canada and other countries. All rights reserved.

© GreenGuard is a Registered Trademark of the Kingspan Group plc in the US. All rights reserved.

[kingspan-green-guard-superstretch-acrylic-flashing-product-data-sheet-en-us-ca-v1](#)

Version 1 - 11/2025

Product Data			
Property		Test Method	Value
Color			Tan
Adhesive Type			Acrylic
Backing Material			Proprietary Film
Water Vapor Transmission	ASTM E96		0.13
Wall Assembly Fire Testd	NFPA 285		5 <sup>1</sup>
Nail Sealability Initial	ASTM E331		Pass
Nail Sealability 127 mm(5 inches) water head after 3 days	ASTM D1970		Dry/Pass
Nail Sealability After Thermal Cycling	ASTM E331		Pass
Adhesive Thickness			0.127 mm (5 mil)
Total Tape Thickness	ASTM D3652		0.25 mm (9.9 mil)
Carrier Thickness	ASTM D3652		0.13 mm (5 mil)
Backing Thickness	ASTM D3652		0.25 mm (5 mil)
Liner			Heavy Paper, split
Application Temperature	AAMA 711-05		-18-66 °C (0 – 150 °F)
Service Temperature Range	AAMA 711-05		-40-116 °C (-40-240 °F)
Elongation at Break	ASTM D882		>700 %
Flame Spread Index	ASTM E84		25

  

90° Peel Adhesion Test Method: ASTM D3330			
Dwell Time	Temperature	Substrate	Value
72 h	23 °C (73 °F)	OSB	6.6 N/cm (60 oz/in) <sup>2</sup>
72 h	23 °C (73 °F)	High Density Polyethylene (HDPE)	6.6 N/cm (60 oz/in) <sup>2</sup>
72 h	23 °C (73 °F)	Housewrap (Spun bonded polyethylene)	5.5 N/cm (50 oz/in) <sup>2</sup>
7 d	80 °C (176 °F)	Anodized Aluminum	7.7 N/cm (70 oz/in) <sup>2</sup>

<sup>1</sup> Pass as part of various assemblies with foam plastic insulation  
<sup>2</sup> 300 mm/min (12 in/min)

To ensure you are viewing the most recent and accurate product information, please visit this link <https://www.kingspan.com/us/en/products/moisture-barrier/flashing-tape/greenguard-superstretch-acrylic-flashing/>

For more information on specific building product recommendations and installation guidelines, contact your Kingspan Insulation LLC representative.

Kingspan Insulation LLC believes the information and recommendations herein to be accurate and reliable. However, since use conditions are not within its control, Kingspan Insulation LLC does not guarantee results from use of such products or other information herein and disclaims all liability from any resulting damage or loss. No warranty, express or implied, is given as to the merchantability, fitness for particular purpose, or otherwise with respect to the products referred to.

